



**TITAN MASONRY CEMENT
MEETS OR EXCEEDS ASTM C-91
MIXING GUIDELINES**

TYPE	TITAN MASONRY 70 lbs	SAND (Arena)		BLOCKS PER BAG (Bloques por Saco)
		PARTS (Partes)	SHOVELS (Palas)	
N	1 BAG	2 1/2 - 3	15 - 18	66 -75

NO ALLOWANCE FOR WASTE
FIELD CONDITIONS MAY CAUSE VARIANCES IN COVERAGE PER BAG

ADD MINIMUM QUANTITY OF CLEAN WATER AND MIX FOR A MINIMUM OF
3 TO 5 MINUTES TO ACHIEVE MORTAR CONSISTENCY FOR PROPER PLACEMENT

TITAN MASONRY CEMENT WHEN MIXED WITH MASONRY SAND
(ASTM C-144) AND TESTED ACCORDING TO THE PROPERTY SPECIFICATION
SECTION OF (ASTM C-270) WILL PRODUCE A MORTAR THAT
COMPLIES WITH THE REQUIREMENTS FOR TYPE 'N' MASONRY.